Made available by Hasselt University Library in https://documentserver.uhasselt.be

Effects of protective panels on charring of timber elements in timber frame assemblies Non Peer-reviewed author version

DE PROFT, Kurt; STEENSELS, Rik & VANDOREN, Bram (2017) Effects of protective panels on charring of timber elements in timber frame assemblies. In: International Journal of Computational Methods and Experimental Measurements, 5(6), p. 797-806.

DOI: 10.2495/CMEM-V5-N6-797-806 Handle: http://hdl.handle.net/1942/25081

EFFECTS OF PROTECTIVE PANELS ON CHARRING OF TIMBER ELEMENTS IN TIMBER FRAME ASSEMBLIES

K. DE PROFT¹, R. STEENSELS² AND B. VANDOREN² ¹WOOD.BE – Belgian Institute for Wood Technology, Hof ter Vleestdreef 3, 1070 Brussels ²Hasselt University – Faculty of Engineering Technology, Martelarenlaan 42, 3500 Hasselt

ABSTRACT

Panels protect timber elements in timber frame assemblies during fire. The influence of the panels can be incorporated into calculations according to EN 1995-1-2, Annex C. The number of panels incorporated in this standard is limited. Moreover, the calculations performed according to this standard result in overestimation of the charred area. In this work, experimental analysis of the protective behaviour was performed. Small scale fire tests were used to monitor the temperature inside the timber element and the timber frame assembly. The measured results are compared with calculations according to the standard.

Keywords: Timber frame construction, fire design, protective panels

1 INTRODUCTION

Eurocode 5 (EN 1995-1-2) provides rules for structural fire design of timber structures. More specific, annex C introduces calculation rules for timber frame assemblies whose cavities are completely filled with insulation.

An important issue in the behaviour of timber frame assemblies during fire is the protection of the timber by panels. EN 1995-1-2 incorporates a methodology to take the effect of protecting panels into account.

The methodology is based on two important parameters related to the specific panel. The first parameter is the time of start of charring, t_{ch} . The time of start of charring describes the time that the timber element, protected by the panel, starts to char. More precisely, the time of start of charring is defined when the temperature behind the panel reaches 300°C. The second parameter is the time of failure of the protection, t_f .

For the moment, only a limited number of panels are referenced in EN 1995-1-2. In this paper, the charring of timber protected by different types of panels is studied experimentally. Small scale fire tests are performed to study the behaviour of the panels and the behaviour of the protected timber element. A large number of thermocouples are positioned in the timber frame assembly and in the timber element in order to follow the temperatures at different locations at different times. All timber frame assemblies are filled with stone wool insulation.

2 DESIGN MODEL IN EN 1995-1-2

The cladding protecting the timber element is characterized by two parameters: the time of start of charring t_{ch} and the time of failure of the protection t_f . The time of start of charring is the time that the timber element, protected by the panel, starts to char. More

precisely, the time of start of charring is defined when the temperature behind the panel reaches 300°C. The time of failure is reached when the panel fails or when the connection of the panel fails so that the panel falls down.



Figure 1: Definition of d_{char}.

It is clear that the timber element is completely protected as long is the time of start of charring is not reached. When the time of start of charring is reached, the timber element starts to char. However, as long as the failure time of the panel is not reached, the timber element is still partly protected by the panel. The depth of charring d_{char} (see definition in figure 1) for this case ($t_{ch} \le t \le t_f$) is given by:

$$d_{char} = k_s k_2 \beta_0 (t - t_{ch}) \tag{1}$$

with k_s the cross-section factor, k_2 the insulation factor and β_0 the one-dimensional charring rate. The one-dimensional charring rate is $\beta_0 = 0,65$ mm/min for solid softwood with a minimal characteristic density of 290 kg/m³.

When the time of failure of the panel is reached $(t > t_f)$, the charring depth d_{char} can be found by:

$$d_{char} = k_s k_3 \beta_0 (t - t_f) + k_s k_2 \beta_0 (t_f - t_{ch})$$
(2)

with k_3 the post protection factor.

The cross-section factor k_s takes the effect of the two dimensional thermal heat transfer into account. The factor is given in EN 1995-1-2 for different widths of the timber element.

b (mm)	k _s		
D (IIIII)	EN 1995-1-2	Relation [2]	
38	1,4	1,81	
45	1,3	1,63	
60	1,1	1,32	

Table 1: Cross-section factor for different widths of the timber frame member.

More conservative values for the cross-section factor are introduced in [2]. An experimental study showed that the stone wool insulation provides less protection of the wide sides of the timber elements. The following expression was proposed for the cross-section factor [2] for a timber element width b between 38 mm and 90 mm:

$$k_s = 0,00023b^2 - 0,045b + 3,19$$
(3)

The insulation factor k₂ is given by:

$$k_2 = 1,05 - 0,0073h_p \tag{4a}$$

$$k_2 = 0,86 - 0,0037h_p \tag{4b}$$

where expression (4a) is for configurations without panel joints on the timber member and expression (4b) is for configurations with panel joints on the timber member.

The post-protection k₃ is given by:

$$k_3 = 0,036t_f + 1 \tag{5}$$

For wood-based panels, the time of start of charring and the time of failure are equal and given by:

$$t_{ch} = t_f = \frac{h_p}{\beta_0} - 4 \tag{6}$$

For gypsum plasterboards of type A and type H, the time of start of charring and the time of failure are equal and given by:

$$t_{ch} = t_{f} = 2,8h_{p} - 14 \tag{7}$$

For gypsum plasterboards of type F, the charring time is given by expression (7). The time of failure is a parameter that should be declared by the manufacturer.

3 EXPERIMENTAL STUDY

3.1 Test set-up

Small scale fire tests are performed on 4 different wall configurations. Within these configurations, the width of the timber element and the protective panels are altered. The test specimens are $1,2m \ge 1,2m$. Two configurations have one intermediate stud with a width of 60 mm. Two configurations have two intermediate studs with a width of 28 mm. The height of all studs is 120 mm. The cavity between the studs is filled with stone wool insulation with a density of 35 kg/m³ or 45 kg/m³. The following table shows an overview of the different configurations that were tested. The back side of all configurations was covered by a vapour open foil.

Table 2: Overview of the tested configurations.

	Panel type	Panel	Stud	Density
		thickness	width	insulation
		(mm)	(mm)	(kg/m³)
1	Gypsum plasterboard (type F)	15	60	35
2	Particleboard (type P5 - fire retardant)	22	28	45
3	Gypsum plasterboard (type H) +	12,5 + 12	28	45
	particleboard (type P5 – fire retardant)			
4	Gypsum plasterboard (type A) + woodfibre	12,5 + 50 + 18	60	35
	board + OSB (type 3)			

In all tests, the panels are oriented to the exposed side. The ISO-fire curve was used to simulate the fire.

In each configuration, a large number of thermocouples were used in order to measure the temperature evolution in function of the time. Figure 2-5 show the different locations of the thermocouples for the different configurations. The temperatures are measured each minute.



Figure 2: Positioning of thermocouples for configuration 1.



Figure 3: Positioning of thermocouples for configuration 2.



Figure 4: Positioning of thermocouples for configuration 3.



Figure 5: Positioning of thermocouples for configuration 4.

3.2 Experimental results

The average temperature behind the panel is calculated over all thermocouples that are positioned at the back side of the panel and shown in figure 6. For clarity, also the ISO-fire curve is plotted in the figure.



Figure 6: Average temperature behind the panel as a function of time.

Clearly, the charring of the timber elements is postponed for all panels. The time of start of charring t_{ch} can be derived from the measured temperatures. Table 3 summarizes for all configuration the time when the temperature behind the panel reaches 300°C.

The time of failure can also be derived from the measurements. However, this is more difficult. The time of failure can be defined in different ways. The time of failure can be determined as the time when the difference between the measure temperature behind the panel and the ISO-fire curve is less than 50K. Further, the time of failure is also reached when big parts of the panel fail. When examining the measured temperatures, failure cannot be determined.

Apart from the temperature behind the panel, the temperatures in the timber element are also measured. From the measurements, the evolution of the 300°C isotherm can be followed. Figure 7 shows the position of the 300°C isotherm at 60 minutes for configuration 1. The temperatures for the remaining section are also shown.

Figure 8 shows the evolution of the charred area (d_{char}) in function of time for all configurations. Examining these figures, all curves can be divided into three parts. In the first part, no charring is present ($d_{char} = 0$). In the second part, the timber element starts charring. The rate of charring is nearly constant. In the third part, the charring continues but with an increase charring rate. The second part can be related to the insulation factor k_2 . The timber is charring but still protected by the panel. The third phase is the post-protection phase, related to k_3 , where the panel has failed. Based on this reasoning, the time of failure can be defined as the time where the rate of charring changes. This definition is used to determine the time of failure in table 3.



Figure 7: Temperature distribution in the timber element at 60 minutes for configuration 1.



Figure 8: d_{char} as a function of time for the different configurations.

	Configuration	Panel thickness	t _{ch}	$t_{\rm f}$
		(mm)	(min)	(min)
1	Gypsum plasterboard (type F)	15	27,4	52
2	Particleboard (type P5 - fire retardant)	22	34,5	51
3	Gypsum plasterboard (type H) + particleboard (type P5 – fire retardant)	12,5 + 12	43,4	58
4	Gypsum plasterboard (type A) + woodfibre	12,5 + 50 + 18	42,4	56
	board + OSB (type 3)			

Table 3: Overview of the tested configurations.

4 COMPARISON BETWEEN EXPERIMENTAL AND COMPATIONAL RESULTS

In this part, the experimental values are compared with computational results using EN 1995-1-2. Configurations 1, 2 and 4 are studied in detail. Some thermocouples in configuration 3 stopped working during the test so that no acceptable results can be shown.

Figure 9 shows the evolution of d_{char} in function of time for configuration 1. The timber element starts charring at t = 27,4 minutes, which corresponds with the t_{ch} = 28 minutes calculated with EN 1995-1-2. The measured charring rate is however lower than the rate predicted with EN 1995-1-2. The insulation factor k_2 is consequently overestimated. Once the panel failed, t_f = 52 minutes, the charring rate increases. The increase predicted by EN 1995-1-2 is again overestimated. Figure 9 also shows a curve with fitted k_2 and k_3 parameters.



Figure 9: d_{char} as a function of time for configuration 1.

Figure 10 shows d_{char} as a function of time for configuration 2. The timber element starts charring at t = 34,5 minutes. The time of charring calculated with EN 1995-1-2 is $t_{ch} = 24,3$ minutes, which is more conservative. An important parameter for the calculation of t_{ch} is the characteristic panel density. The panel used in the test has a higher density explaining the big difference. EN 1995-1-2 assumes the time of failure equal to the time of start of charring. Clearly, this is not the case in het experiment. Consequently, the d_{char} calculated with EN 1995-1-2 would result in an overestimation. Contrary to configuration 1, the insulation factor k_2 gives a better estimation. The post-protection factor is again overestimated. Figure 10 also shows a curve with fitted k_2 and k_3 parameters.



Figure 10: d_{char} as a function of time for configuration 2.

Figure 11 shows the d_{char} as a function of time for configuration 4. Due to the specific combination of panels, the time of start of charring cannot be predicted with EN 1995-1-2. Contrary to the previous configurations, a fourth phase can be identified in the figure. The timber starts charring at $t_{ch} = 42,4$ minutes. The panels fail at $t_f = 56$ minutes, where a sudden increase in charring rate is observed. The insulation factor k_2 gives a good estimation for the charring rate between t_{ch} and t_f . The post protection factor k_3 is again overestimated. After 65 minutes, the charring rate decreases again. At that time, the char layer forms an insulation layer protected the timber element.



Figure 11: d_{char} as a function of time for configuration 4.

5 CONCLUSIONS

In this paper, the effect of protective panels on the charring of timber elements in timber frame assemblies was studied. Different wall configurations using different protective panels were tested in small scale fire tests. During these tests, the temperature evolution was followed at different location.

Thermocouples positioned behind the panels made it possible to determine the time of start of charring. Time of failure of the panel is more difficult to monitor based on these thermocouples.

Thermocouples positioned inside the timber element made it possible to follow the temperature inside the element and detect the 300°C isotherm in function of time. Timber is assumed to char at 300°C. Based on the charring rate, the time of failure can be determined. EN 1995-1-2 assumes the time of start of charring and the time of failure equal for wood based panels. Experiments show that there is a difference.

The measured charring rates are compared with the calculation model proposed in EN 1995-1-2. Two factors, the insulation factor k_2 and the post-protection factor k_3 , are evaluated. In most cases, the insulation factor gives a good estimation of the charring rate between time of start of charring and time of failure. The post-protection factor resulted for

all experiments in an overestimation. Furthermore, it was observed that the charring rate decreases again once a sufficient char layer was formed. More experiments will be done to examine the effect of the thickness of this char layer.

ACKNOWLEDGEMENTS

The authors would like to acknowledge NBN (www.NBN.be) for the financial support to this project.

REFERENCES

- [1] EN 1995-1-2, Design of timber structures: part 1-2: General structural fire design, 2009.
- [2] Just A., *The effect of insulation on charring of timber frame members*, SP Report 2010:30, Stockholm, 2010.